




Certified MS
ISO 9001:2015
No. Cert. 1118/Δ/2019



DESCRIPTION




Gboard[®] MR H2 is a moisture resistant board having a reasonable percentage, between 5 to 10 %, of water absorption. The silicon oil in its core acts as a water repellent rendering it more resistant to moisture. Gboard[®] MR H2 is the perfect suit for areas of high humidity.

Gboard[®] MR H2 is composed of the best quality gypsum, non-toxic minerals, and moisture repellent additives which suit health conditions.

All materials are certified based on ASTM and EN standards and tested in approved laboratories.



PROPERTIES

SURFACE FINISHING	EDGE TYPES	STANDARDS	DIMENSIONS
Painted (water or oil base paint)	Squared edge 	ASTM C 1396	Width 1200mm, 1220mm
Cladding (wallpaper, vinyl, wood...)	Tapered edge 	ASTM C 473	Length 2000mm, 2400mm, 2440mm, 2500mm, 3000mm
Joint filling with Gcoat [™] All Purpose Joint Compound	Beveled edge 	EN 520	Thicknesses 8.0mm, 9.5mm, 12.5mm, 15mm, 15.9mm, 18mm
			*Varying dimensions available upon request

APPLICATIONS

- Reception areas
- Meeting rooms, conference rooms
- Cafeterias, restaurants
- Toilets, humid areas
- Showrooms, office buildings
- Malls, lounges, shops

FEATURES

- Thermally balanced
- Highly resistant to cracks
- Low moisture absorption rate
- Suitable sound insulation
- Easy to handle and install
- Lightweight
- Eco-friendly, recyclable



Moisture resistant



Durable



Sound insulation



No cracking

PHYSICAL SPECIFICATIONS

SPECIFICATIONS	UNIT	VALUE	STANDARD
Thickness	mm	12.5	ASTM C 1396
Density	Kg/m ³	675	ASTM C 1396
Weight per unit area	Kg/m ²	7.9-8.5	ASTM C 1396
Tolerance of length	mm	2401 (±1)	ASTM C 1396
Tolerance of width	mm	1200 (0-2)	ASTM C 1396
Tolerance of thickness	mm	12.5 (±2)	ASTM C 1396
Ends squareness	mm	±2	ASTM C 1396
Depth of taper	mm	0.7-1.1	ASTM C 1396
Width of taper	mm	40-45	ASTM C 1396
Core hardness	N	110-160	ASTM C 1396
Edges hardness	N	110-160	ASTM C 1396
Ends hardness	N	110-160	ASTM C 1396
Flexural breaking load long edge	N	550-600	ASTM C 1396
Flexural breaking load short edge	N	210-240	ASTM C 1396
Nail pull strength	N	360-440	ASTM C 1396
Moisture content	%	5-10	ASTM C 1396
Total water absorption	%	8-10	EN 520
Surface water absorption	g/m ²	160-180	EN 520

RECOMMENDATION

- Cutting and scoring are completed from the front face of the board.
- Use phosphate plated self-tapping screws with a metal frame <0.7mm for board fixing.
- Use phosphate plated self-drilling for a metal frame >0.7mm for board fixing.
- Vertical screw spacing for the first layer of gypsum is 25cm, 50cm for the second, and 75cm for the third.
- It is recommended to use Gcoat™ All Purpose Joint Compound to treat joints or for skim coating.

STORAGE AND HANDLING

- Avoid contact with water or temperatures higher than 50°C for prolonged periods of time.
- Store in a dry/ventilated area above ground level (not in direct contact with the ground).
- Cover the boards with plastic sheets.
- Avoid direct rain or sunlight.
- Avoid cracking or damaging the boards during installation.

Société SARL au capital 100.000.00 RC: 144275
Patente : 29502645 IF: 30463370- CNSS: 6435569
ICE: 002908309000092, renovbatiisarl@gmail.com ; Tél: 0661706980
S,social :lmm n°50App n° 10 rue Moulay Ahmed LoukiliHassan Rabat
site web: <https://www.placomaroc.net>